

HYDROTEX 2.0 is approved by Network Rail– Certificate No PA05/05451

Mechanical Properties (Mean Values)			
Wide– Width Strip Tensile			
• Mean pick strength	EN ISO 10319	kN/m	95
• Elongation at peak strength		%	75
CBR Puncture Resistance			
• Mean peak strength	EN ISO 12236	kN	18
Cone Drop			
• Mean hole diameter	EN 13433	mm	0
Filter Properties			
Pore Size <sup>[1]</sup> - Mean AOS	ASTM F316-03 (2011)	µm	<1
Permeability			
• V <sub>l280</sub>	EN ISO 11058	m/s	1 x 10 <sup>-5</sup> (min 5 x 10 <sup>-6</sup> )
• 0.28m Head			
Physical Properties (Typical Values)			
Weathering			
• Retained strength at 200MJ/m <sup>2</sup> exposure	EN 12224	%	>90
Microbiological Resistance			
• Retained Strength	EN 12225	%	No Loss <sup>[2]</sup>
Resistance to Acids & Alkalis			
• Retained Strength	EN 14030	%	No Loss <sup>[2]</sup>
Oxidation			
• Retained strength at 85 days	EN ISO 13438	%	>80

1. ASTM F316-3 has been used as an alternative to ISO12956 to allow for accurate measurement of a micro– porous nonwoven.
2. No loss identifiable as a result of exposure– sample variation could still result in a variable loss.

### Durability

This product is predicted to be durable for more than 100 years in soil with a pH in the range 2 to 14 and with a temperature of less than 25° C.

### Chemical resistance

Polypropylene and polyethylene are unaffected by the chemicals which normally exist in soils.

### Biological resistance

Polypropylene and polyethylene are not nutrients for micro-organisms and do not provide nourishment for animals & insects.

### UV exposure

Fiberweb Geosynthetics' products are delivered to site in polyethylene wrapping to protect against the effects of ultra-violet radiation. It is recommended that the products remain wrapped until their installation.

Once unwrapped, the products should be completely covered with the fill within 14 days to avoid exposure to UV radiation.

Versions of most products can be manufactured with enhanced UV performance by incorporating stabilisers. These versions carry the suffix UV. The remaining properties are identical to the corresponding standard grade.

Adequate precautions should always be taken to protect all products from UV radiation to achieve the stated durability.

### Notes:

1. Refer to the *Terram Jointing Methods* (downloadable from [www.terram.com](http://www.terram.com)) for when simple overlaps are required for subsequent and adjacent roll lengths. However, pegging, sewing, stapling or gluing can also be used depending upon the application, the sub-grade conditions, the loading, the convenience and the cost.
2. These figures relate to standard product weights and roll sizes. Other weights, sizes and colours may be available on request. For further information please contact Fiberweb Geosynthetics' Technical Support.



As part of its continual improvement process Fiberweb Geosynthetics Ltd reserve the right to change the properties listed on this data sheet without prior notice.

™ indicates a trade mark of Berry Global, many of which are registered in a number of countries around the world.



A Berry Global Company  
Fiberweb Geosynthetics Ltd  
Blackwater Trading Estate  
The Causeway, Maldon, CM9 4GG  
United Kingdom

Tel: +44 (0)1621 874200  
Fax: +44 (0)1621 874299  
Email: [info@terram.com](mailto:info@terram.com)  
[www.terram.com](http://www.terram.com)



# TERRAM

Geosynthetics you can trust