

### DESCRIPTION:

A cellular confinement system fabricated from strips of high strength nonwoven TERRAM geotextile with chemically bonded joints. The TERRAM geotextile strips are manufactured from UV stabilised, high tenacity, virgin polypropylene fibres that have been both mechanically and thermally bonded to give high strength and permeability.

### APPLICATIONS:

Manufactured for over 20 years TERRAM Geocells provide full depth mechanical stabilisation/reinforcement of generally unbound soil fill layers. Typical uses include:-

- Slope erosion control for topsoil and vegetation.
- Subbase confinement of granular fills particularly Tree Root Protection (TRP) and Sustainable Drainage Systems (SuDS).
- Retaining structures using multiple horizontal and stacked layers.



### FEATURES & BENEFITS:

- Made from inert polymers giving excellent long term durability in all soil types.
- Fully permeable geotextile allows water movement in all directions preventing surface water cascading over cells and piping through punched holes in cell walls.
- Stabilises fill reducing the amount of imported material required reducing costs.
- Reduces bearing pressures helping to control differential settlement in soft and variable strength ground.
- British manufactured with a low transport carbon footprint for UK deliveries
- Lightweight flexible material which hugs ground contours and is easy to handle, cut and install.





### INTENDED USE/FUNCTIONS:



### INTENDED APPLICATIONS:



PHYSICAL PROPERTIES	Test Method	Unit	Panel Grades					
			22/20	22/25	25/10	25/15	35/10	35/15
Cell Diameter		mm	220	220	250	250	350	350
Cell Length (L)		mm	275	275	295	295	415	415
Cell Width (W)		mm	230	230	250	250	370	370
Cell Depth		mm	200	250	100	150	100	150
Approximate cells per SQM			30	30	26	26	12	12
Colour			Grey	Grey	Grey	Grey	Grey	Grey
MECHANICAL/HYDRAULIC PROPERTIES								
Cell Wall Permeability—(H50)	EN ISO 11058	l/m <sup>2</sup> s	20	20	20	20	20	20
Cell Wall Tensile Strength	EN ISO 10319	kN/m	22.0	22.0	22.0	22.0	22.0	22.0
Cell Junction Peel Strength	Internal test method	kN/m	9.0	9.0	9.0	9.0	9.0	9.0
DURABILITY PROPERTIES								
Weathering (UV Exposure)	EN 12224	Days	30	30	30	30	30	30
Combined ageing (Oxidation, temperature & moisture)	EN ISO 13438	Service Life (Years)	100	100	100	100	100	100
PANEL DIMENSIONS								
Panel Length		m	6.2	3.2	7.3	7.3	7.4	7.4
Panel Width		m	3.2	6.2	5.1	5.2	5.2	5.2
Panel Weight		kg	20	25	17	25	11	17
Panels per pallet			12	12	18	12	30	14
Gross pallet weight		kg	233	241	320	395	218	252

#### PACKAGING & IDENTIFICATION

Terram Geocell panels are supplied flat packed on pallets with banding straps and identification labels.

#### STORAGE

Geocell panel pallets shall be stored on stable/ level ground, stacked not more than two packs high and no other materials shall be placed on top. Can be stored outdoors when packaged, but should be protected from exposure to UV. All materials should be stored in accordance with good health and safety practice and in accordance with local laws.

#### QUALITY

Terram Geocells are supplied having met internal quality requirements in accordance with our Quality Management system which is certified to BS EN ISO 9001:2015.

#### NOTES


Reported values are nominal unless otherwise stated. Reported values related to durability testing are generally based on the lowest grade of Terram geotextile within a family.

#### ADDITIONAL INFORMATION

Gross pallet weight is provided is for lifting guidance only, it does not form part of quality control procedures.

Refer to the Terram Specification, Design and Installation guides for advice on product grade selection, installation, fixing, jointing and filling.

These figures relate to standard product weights and pack sizes. Other weights, sizes and colours may be available on request. For further information please contact Terram Customer Services as detailed below.



How else can we help? Get in touch with us

+44 (0) 1621 874200    info@terram.com    www.terram.com

